Epitex-C-9901-21-50

Epoxy Ester

Epitex-C-9901-21-50 is a siliconized epoxy ester supplied at 50% solids in a solvent combination of xylene and VM&P Naphtha. It is suggested for use in air-dry or forced dried industrial applications. Those include rust inhibitive primers, zinc-rich primers, enamels, and clear coats. Epitex-C-9901-21-50 is ideal for optimum performance in a single package system.

Physical State
Liquid

Applications
- Corrosion Resistant Industrial Coating

Advantages
- Good adhesion
- Corrosion Resistance
- Chemical and Heat Resistance

Typical Properties

Viscosity (Gardner-Holdt)	**W - Z**
Color (Gardner)	**8 max.**
Acid Value	**15 mg KOH/g max.**
Solids	**50 ± 2%**
Density	**8.10 ± 0.15 lb/gal**
Solvent	**Xylene**
	VM&P Naphtha
	Isopar L

Recommended Driers (metal on resin solids)

Air Dry:
0.2% - 12% Zirconium
0.1% - 12% Cobalt
Baked Dry:
15% (Total Solids) Amino resin

Shelf Life: 2 years in a sealed container at 77°F.

Precautions
Some materials in this product may cause skin and eye irritation and/or sensitization or other allergic responses upon repeated contact. Therefore, this product must be handled with extreme care and in strict adherence to good industrial practices. Before using it or any other product referred to in this bulletin, consult the applicable Safety Data Sheets for appropriate handling procedures and protective equipment.

Revision Date: Sept 1, 2026

THE INFORMATION PRESENTED HEREIN, WHILE NOT GUARANTEED, IS TO THE BEST OF OUR KNOWLEDGE TRUE AND ACCURATE. NO WARRANTY OR GUARANTEE EXPRESSED OR IMPLIED IS MADE REGARDING THE PERFORMANCE OF ANY PRODUCT, SINCE THE MANNRT OF USE IS BEYOND OUR CONTROL. NO SUGGESTION FOR PRODUCT USE, NOR ANYTHING HEREIN, SHALL BE CONSTRUED AS A RECOMMENDATION FOR ITS USE IN INFRINGEMENTOF ANY EXISTING PATENT

Revision 2026-08-31

300 East Primm St. | St. Louis, MO 63111 | (314) 638-1632 | Fax: (314) 638-3100 | www.uspolymers.com