HPP-E-9968-22-50 (Preliminary TDS)

Medium Oil Alkyd

HPP-E-9968-22-50 is a medium soya oil alkyd designed for use in a variety of architectural and industrial finishes along with traffic paints. HPP-E-9968-22-50 can be used in clear or pigmented applications.

Physical State
Liquid

Applications
- Architectural
- Implement
- Structural
- TT-P-636 Primer

Advantages
- Air Dry or Bake
- Good Color Retention
- Good Gloss Retention
- Good Flexibility

Operating Data:
1. Designed for brush, spray, dip, and roller applications
2. Reduce viscosity as needed for roll or spray

Typical Properties*

Viscosity (Gardner-Holdt)	**Z8-Z10**
Color (Gardner)	**8 max.**
Acid Value	**20 mg KOH/g max.**
Solids	**50 ± 2%**
Density	**7.75 ± 0.15 lb/gal**
Solvent	**Mineral Spirits**

*Specifications are subject to change based on results when product is made commercially following multiple production batches. Preliminary data for this sheet was based on laboratory conditions.

Recommended Driers (Metal on resin solids)

Air Dry: 0.2% Zirconium
0.05% Cobalt

Bake: 0.01% - 0.02% Manganese

Note: Avoid excess mixing and air introduction during blending with drier

Shelf Life: 2 years in a sealed container at 77°F.

Revision Date: 9/1/2026

Precautions
Some materials in this product may cause skin and eye irritation and/or sensitization or other allergic responses upon repeated contact.Therefore, this product must be handled with extreme care and in strict adherence to good industrial practices. Before using it or any other product referred to in this bulletin, consult the applicable Safety Data Sheets for appropriate handling procedures and protective equipment.

THE INFORMATION PRESENTED HEREIN, WHILE NOT GUARANTEED, IS TO THE BEST OF OUR KNOWLEDGE TRUE AND ACCURATE. NO WARRANTY OR GUARANTEE EXPRESSED OR IMPLIED IS MADE REGARDING THE PERFORMANCE OF ANY PRODUCT, SINCE THE MANNRT OF USE IS BEYOND OUR CONTROL. NO SUGGESTION FOR PRODUCT USE, NOR ANYTHING HEREIN, SHALLBE CONSTRUED AS A RECOMMENDATION FOR ITS USE IN INFRINGEMENTOF ANY EXISTING PATENT

300 East Primm St. | St. Louis, MO 63111 | (314) 638-1632 | Fax: (314) 638-3100 | www.uspolymers.com