HPP 8378

High Solids, Phenolic Modified Alkyd

HPP 8378 is a high solids phenolic modified alkyd resin designed for air-dry industrial maintenance type finishes. HPP 8378 gives salt spray resistance and topcoat lift resistance.

Physical State
Liquid

Applications
- Air Dry Industrial Maintenance

Advantages
- Salt Spray Resistance
- Topcoat Lift Resistance

Operating Data
1. Designed for brush, spray, and roller applications.
2. Reduce viscosity as needed for roll or spray.

Typical Properties

Viscosity (Gardner-Holdt)	**Z – Z2**
Color (Gardner)	**12 max.**
Acid Value	**20 mg KOH/g max.**
Solids	**75 ± 2%**
Density	**9.00 ± 0.15 lb/gal**
Solvent	**n-Butyl Acetate**

Shelf Life: 2 years in a sealed container at 77°F.
When container is opened, it must be nitrogen blanketed or it will skin.

Precautions
Some materials in this product may cause skin and eye irritation and/or sensitization or other allergic responses upon repeated contact. Therefore, this product must be handled with extreme care and in strict adherence to good industrial practices. Before using it or any other product referred to in this bulletin, consult the applicable Safety Data Sheets for appropriate handling procedures and protective equipment.

Revision Date: Sept 1, 2026

THE INFORMATION PRESENTED HEREIN, WHILE NOT GUARANTEED, IS TO THE BEST OF OUR KNOWLEDGE TRUE AND ACCURATE. NO WARRANTY OR GUARANTEE EXPRESSED OR IMPLIED IS MADE REGARDING THE PERFORMANCE OF ANY PRODUCT, SINCE THE MANNER OF USE IS BEYOND OUR CONTROL. NO SUGGESTION FOR PRODUCT USE, NOR ANYTHING HEREIN, SHALL BE CONSTRUED AS A RECOMMENDATION FOR ITS USE IN INFRINGEMENTOF ANY EXISTING PATENT

300 East Primm St. | St. Louis, MO 63111 | (314) 638-1632 | Fax: (314) 638-3100 | www.uspolymers.com