Valtex-F-8974-23-75

Phenolic Tung Oil Primer

Valtex-F-8974-23-75 is a high quality phenolic modified tung oil varnish intended to be employed as a lift resistant primer or for fortifying alkyds in terms of corrosion protection. Valtex-F-8974-23-75 primers provide excellent chemical resistance. It also provides water resistance as well as resistance to fat and grease. This primer is an air-dry system. Valtex-F-8974-23-75 can be used as the sole resin binder.

Physical State
Liquid

Applications

- Primer for Direct to Metal (DTM)
- Stand Alone Binder for DTM
- Offset Inks/Coatings

Advantages

- Conducive to recoat using paint containing strong solvent.
- Fast Dry and Recoat Times
- Excellent Chemical Resistance
- Unmatched Corrosion Protection

Operating Data

1. Designed for brush, spray, and roller applications.
2. Reduce viscosity as needed for roll or spray.
3. 10 cc per gallon of anti-skinning agent is recommended (ASA).

Typical Properties

Viscosity (Gardner-Holdt)	**To be determined.**
Color (Gardner)	**12 max.**
Solids	**75 ± 2**
Density	**To be determined ± 0.15 lb/gal**
Solvent	**n-Butyl Acetate**

Recommended Driers (Metal on resin solids)

0.1% 12% Cobalt
0.2% 12% Zirconium

Shelf Life: 2 years in a sealed container at 77°F.
When container is opened, it must be nitrogen blanketed or it will skin.

Precautions
Some materials in this product may cause skin and eye irritation and/or sensitization or other allergic responses upon repeated contact. Therefore, this product must be handled with extreme care and in strict adherence to good industrial practices. Before using it or any other product referred to in this bulletin, consult the applicable Safety Data Sheets for appropriate handling procedures and protective equipment.

Revision Date: Sept 1, 2026

THE INFORMATION PRESENTED HEREIN, WHILE NOT GUARANTEED, IS TO THE BEST OF OUR KNOWLEDGE TRUE AND ACCURATE. NO WARRANTY OR GUARANTEE EXPRESSED OR IMPLIED IS MADE REGARDING THE PERFORMANCE OF ANY PRODUCT, SINCE THE MANNER OF USE IS BEYOND OUR CONTROL. NO SUGGESTION FOR PRODUCT USE, NOR ANYTHING HEREIN, SHALL BE CONSTRUED AS A RECOMMENDATION FOR ITS USE IN INFRINGEMENTOF ANY EXISTING PATENT

300 East Primm St. | St. Louis, MO 63111 | (314) 638-1632 | Fax: (314) 638-3100 | www.uspolymers.com