Valtex 728

Phenolic Tung-Linseed Oil Varnish

Valtex 728 is a pure phenolic tung-oil varnish.

Physical State
Liquid

Applications

- MIL-V-15218B, Type II
- MIL-P-15145B
- TT-P-641F, Type III

Operating Data

1. Designed for brush, spray, and roller applications.
2. Reduce viscosity as needed for roll or spray.
3. 10 cc per gallon of skinning agent is recommended (ASA)

Typical Properties

Viscosity (Gardner-Holdt)	**L - N**
Color (Gardner)	**12 max.**
Solids	**60 ± 2%**
Density	**7.40 ± 0.15 lb/gal**
Solvent	**Mineral Spirits**

Recommended Driers (Metal on resin solids)

0.1% - 12% Cobalt
0.2% - 12% Zirconium

Shelf Life: 2 years in a sealed container at 77°F.
When the container is opened, it must be nitrogen blanketed or it will skin.

Revision Date: 9/1/2026

Precautions
Some materials in this product may cause skin and eye irritation and/or sensitization or other allergic responses upon repeated contact. Therefore, this product must be handled with extreme care and in strict adherence to good industrial practices. Before using it or any other product referred to in this bulletin, consult the applicable Safety Data Sheets for appropriate handling procedures and protective equipment.

THE INFORMATION PRESENTED HEREIN, WHILE NOT GUARANTEED, IS TO THE BEST OF OUR KNOWLEDGE TRUE AND ACCURATE. NO WARRANTY OR GUARANTEE EXPRESSED OR IMPLIED IS MADE REGARDING THE PERFORMANCE OF ANY PRODUCT, SINCE THE MANNRT OF USE IS BEYOND OUR CONTROL. NO SUGGESTION FOR PRODUCT USE, NOR ANYTHING HEREIN, SHALL BE CONSTRUED AS A RECOMMENDATION FOR ITS USE IN INFRINGEMENTOF ANY EXISTING PATENT

300 East Primm St. | St. Louis, MO 63111 | (314) 638-1632 | Fax: (314) 638-3100 | www.uspolymers.com